

## Cowa PCM 58


Salt hydrate based phase change material

### Material Properties

Phase transition temperature	°C	57
Enthalpy*	kJ/kg	260
Specific heat capacity (liq.)	kJ/kg*K	2.57
Density (liq.)	kg/m <sup>3</sup>	1460
Thermal conductivity	W/m*K	0.66
Corrosion	-	Not corrosive in combination with the copper, aluminium

\*measured with 3-Layer

### 3-Layer Experiment



We are constantly developing and improving our materials. All product specifications, statements, information and data in this datasheet or on the website are therefore subject to change.

Contact:

Cowa Thermal Solutions AG  
 Technopark Luzern Platz 4  
 CH6039 Root D4  
 info@cowa-ts.com  
 www.cowa-ts.com